

BODY PRIMER, GROUND BY TUDHOPE CARRIAGE CO.

MARCH 15, 1913.

March 15, 1913.

Mar. 15/13.

83½ lbs. Dry White lead	@5.65 per 100 lbs.	\$5.55
16 2/3 lbs. Bolted Whiting	@ .90 " " gal.	.15
10 lbs. Keystone Filler	@1.55 " " "	.16
6 " Lamp Black	@.6½ " lb.	.39
3½ Gal. Prepared Oil	@ .67 per gal.	2.34
3 1/3 gal. Mixing Japan	@ 1.00 " " "	3.33
1 ½ " " Varnish	@1.25 " " "	1.87
10 gal. Raw Linseed Oil	@.56½ " " "	5.65
4½ " Turpentine	@63¼ " " "	2.87
1½ " Benzine	@.24 " " "	.36

22.67

Mixing, Grinding and Reducing 3 Hrs. @ 20¢ .60  
55% O.H. .33

.93

1 qt. Carriage Rubbing Varnish @ 1.55 gal. 23.60

1 " Mixing Japan @1.00 " .25

1 lb. Lead ground in oil 26¢ per lb. .27

1 " Lamp Black 26¢ per lb. .04

24 1/3 Gal. Liquid 23.60

116 lbs. Pigment 2.00

Above yields;-

27 Gal. Body Primer @ 23.60 87¢ per gal. 23.60

55% O.H. 1.24

Above yields 50 lbs. Putty @5.09 per lb. 10.45