

DARK GEAR FILLER. GROUND BY TUDHOPE CARRIAGE COMPANY.

Mar. 15/13.

105 lbs.	Bolted whiting	@ 90¢ per 100 lbs.		.95
45 "	Dry white lead	@6.65 " "		3.00
14 "	Lamp Black	@6½ " lbs.		.91
9 Gal	Prepared Oil	@67¢ per Gal.		6.03
5 "	Mixing Japan	@1.00 " "		<u>5.00</u>
				15.89
Labor mixing and Grinding.	4 hrs.	@20¢	80	
		55% O.H.	44	<u>1.24</u>
				17.13
Above yields	280 lbs. filler	@17.13	per lb.	6 1/9¢

DARK HARD PUTTY MADE BY TUDHOPE CARRIAGE COMPANY.

Mar. 15/13.

1 qt.	Carriage Rubbing Varnish	@ 1.95 gal.		3.49
1 "	Mixing Japan	@1.00 "		.25
1 lb.	Lead Ground in oil	@6½ ¢ lb.		.07
½ "	Lamp Black	@6½ ¢ lb.		.04
45 "	Dry white lead	@6.65 per 100 lbs.		<u>3.00</u>
				3.85
Labor, mixing etc.	4 hrs.	@20¢	80	
		55% O.H.	44	<u>1.24</u>
				5.09
Above yields	50 lbs. Putty	@5.09	per lb.	10¢