

BODY LEAD GROUND BY TUDHOPE CARRIAGE CO., March 21, 1913.

20	lbs. Crimson Oxide,	@ 2.85 per 100 lbs.	.57
40	" #2 Keystone Filler,	@ 1.55 " " "	.62
1 $\frac{1}{2}$	gal. Mixing Japan,	@ 1.00 " gal.	1.50
50	lbs. Dry White Lead,	@ 6.65 " 100 lbs.	3.32
1	gal. Mixing Varnish,	@ 1.25 " gal.	1.25
5	" Prepared Oil,	@ .67 " "	<u>3.35</u>
			10.61

Mixing & Grinding,	2 Hrs. @ 20 ¢,	40 ¢	
	55 % O. H.	<u>22</u>	<u>.62</u>
			11.23

Total Mix 183 lbs.

Yield of 175 lbs. @ 11.23 per lb. 6-1/2 ¢.